# Inexpensive, Nonfluorinated (or Partially Fluorinated) Anions for Lithium Salts and Ionic Liquids for Lithium Battery Electrolytes

### **Wesley Henderson**

Ionic Liquids & Electrolytes for Energy Storage (ILEET) Laboratory Department of Chemical & Biomolecular Engineering NC State University

May 11, 2011

Project ID# es057

**NC STATE UNIVERSITY** 

This presentation does not contain any proprietary, confidential, or otherwise restricted information



### **Overview**

### **Timeline**

Project Start: April 24, 2009

Project End: March 31, 2012

Percent Completed: 66%

### **Budget**

Total Project Funding:

\$763,057

Funding Received FY10:

\$245,450

Funding Received FY11:

\$245,882

### **Barriers**

Low cost cell materials

Abuse tolerance

Low temperature performance

#### **Partners**

Project Lead: Wesley Henderson

Co-PIs: Michel Armand, Peter Fedkiw

**Collaborators:** 

- Kang Xu, Richard Jow (ARL)
- Patrick Judeinstein (Université Paris-Sud)
- Steve Greenbaum (Hunter College of CUNY )
- Patrik Johansson (Chalmers University)



### **Objectives**

- Develop techniques to synthesize electrolytes that allow for lower cost of production
- Develop low-cost, thermally stable electrolytes to replace ones now commonly used
- Develop electrolyte/additive combinations that will facilitate a more stable solid-electrolyte interphase (SEI) on the anode
- Develop additives that allow for the formation of protective coatings on the cathode (i.e., a cathode SEI) and enhances electrochemical stability above 4.3 V



### **Milestones**

Milestone	Completion
■ Characterization (properties/phase diagrams) of solvent-LiBF <sub>4</sub> mixtures as model electrolytes	ongoing
<ul> <li>Characterization (properties/phase diagrams) of solvent-LiBOB and -LiDFOB mixtures to examine structural effects on solubility/properties</li> </ul>	ongoing
Synthesis/characterization of ionic liquids containing cyanocarbanions and DFOB-	ongoing
<ul> <li>Synthesis of new partially fluorinated anions (with new ligands) and cyanocarbanions</li> </ul>	ongoing



### **Approach**

Synthesize and fully characterize two classes of nonfluorinated (or less fluorinated) anions:

- (1) chelated and non-chelated organoborate anions (related to bis(oxalato) borate or BOB<sup>-</sup>), and
- (2) Hückle-type anions in which the charge is stabilized on a 5-member azole ring and noncyclic cyanocarbanions. Characterize the physical properties of these new anions, incorporated in both lithium salts and ionic liquids, by examining the thermal phase behavior (phase diagrams); thermal, chemical and electrochemical stability; transport properties; interfacial properties; molecular interactions and cell performance. These salts will be compared with widely used salts such as LiPF<sub>6</sub> and LiBOB and ionic liquids based upon the bis(trifluoromethanesulfonyl)imide anion (TFSI-).





### **Technical Accomplishments - Overview**

- Prepared phase diagrams of solvent-LiBF<sub>4</sub> mixtures (acetonitrile, adiponitrile) to serve as a model system (for comparison with new salts)
- Synthesized high purity lithium difluoro(oxalato)borate (LiDFOB) determined the crystal structure of the LiDFOB·2H<sub>2</sub>O dihydrate prepared phase diagrams with a variety of solvents including carbonates, esters, sulfones and nitriles/dinitriles numerous LiDFOB solvate crystal structures were determined providing insight into how the anion and solvent molecules interaction with Li<sup>+</sup> cations
- Characterized ionic liquid (IL) properties (conductivity, density, viscosity, diffusion coefficients) for ILs with cyanocarbanions: DCTA<sup>-</sup> (dicyanotriazolate) and DCA<sup>-</sup> (dicyanamide)




## Lithium Difluoro(oxalato)borate (LiDFOB)





Crystal structure of LiDFOB






# LiDFOB-2H<sub>2</sub>O

Crystal structure of LiDFOB dihydrate

CIP (H<sub>2</sub>O)<sub>2</sub>:LiDFOB






# (Solvent)<sub>n</sub>-LiX Mixtures: Ionic Association Interactions

 $\left\langle \right\rangle$ 

- Solvent-Separated Ion Pairs (SSIPs) (uncoordinated anions)
- Contact Ion Pairs (CIPs)
  (anion coordinated to 1 Li<sup>+</sup>)
- Aggregates (AGGs)(anion coordinated to 2 or more Li<sup>+</sup>)

```
LiTFSI, LiPF<sub>6</sub>
LiClO<sub>4</sub>, LiI
LiBF<sub>4</sub>
LiCF<sub>3</sub>SO<sub>3</sub>
LiCF<sub>3</sub>CO<sub>2</sub>
```


increasing association



# ILEET

### **AN-Li<sup>+</sup> Solvation**


 $H_3C$   $\longrightarrow$  N:





LiBF<sub>4</sub>


LiDFOB


C-C stretching mode (920 cm<sup>-1</sup>) C≡N stretching mode (2250 cm<sup>-1</sup>)















Wavenumber (cm<sup>-1</sup>)

LiCF<sub>3</sub>CO<sub>2</sub>




### **Carbonate & Ester Solvents**



ethylene carbonate ( $T_{\rm m}$  35°C,  $T_{\rm b}$  244 C)

propylene carbonate ( $T_{\rm m}$  -55°C,  $T_{\rm b}$  242 C)

 $\gamma$ -butyrolactone ( $T_{\rm m}$  -44°C,  $T_{\rm b}$  204 C)





dimethyl carbonate ( $T_{\rm m}$  5°C,  $T_{\rm b}$  91 C)

diethyl carbonate ( $T_{\rm m}$  -74°C,  $T_{\rm b}$  126 C)




### Ethylene Carbonate (EC)<sub>n</sub>-LiX Phase Behavior









### **Propylene Carbonate (PC)<sub>n</sub>-LiX Phase Behavior**









### γ-Butyrolactone (GBL)<sub>n</sub>-LiX Phase Behavior









# Dimethyl Carbonate (DMC)<sub>n</sub>-LiX Phase Behavior






# LEET


### **Dimethyl Carbonate (DMC)<sub>n</sub>-LiX Phase Behavior**



AGG (DMC)<sub>3/2</sub>:LiDFOB












### Diethyl Carbonate (DEC)<sub>n</sub>-LiX Phase Behavior







### **Sulfone Solvents for High-Voltage Electrolytes**



tetramethylene sulfone ( $T_{\rm m}$  27°C,  $T_{\rm b}$  285 C)





ethyl methyl sulfone ( $T_{\rm m}$  32-37°C,  $T_{\rm b}$ ??? C)

A. Abouimrane, I. Belharouak, K. Amine, *Electrochem. Commun.* **2009**, *11*, 1073



### **Sulfone-LiDFOB Phase Behavior**









# (TMS)<sub>n</sub>-LiDFOB Phase Behavior











### Nitrile/Dinitrile Solvents for High-Voltage Electrolytes




Y. Abu-Lebdeh and I. Davidson, J. Electrochem. Soc. 2009, 156, A60




### Acetonitrile (AN)-LiBF<sub>4</sub> Phase Behavior









### Acetonitrile (AN)<sub>n</sub>-LiBF<sub>4</sub> Phase Behavior












# Acetonitrile (AN)<sub>n</sub>-LiDFOB Phase Behavior









# Acetonitrile (AN)<sub>n</sub>-LiDFOB Phase Behavior











### Acetonitrile (AN)<sub>n</sub>-LiDFOB Phase Behavior


AGG (AN)<sub>1</sub>:LiDFOB









### Adiponitrile (ADN)<sub>n</sub>-LiDFOB Phase Behavior









### Ionic Liquids (ILs)


A number of ILs have been synthesized and their properties are currently being characterized







★ IM<sub>10R</sub>X ILs prepared for comparison with PY<sub>1R</sub>X ILs rather than as electrolyte materials





### **Collaborations/Coordination with Other Institutions**

**Army Research Laboratory (ARL)** – Joshua Allen (a graduate student) spent several weeks last year with Kang Xu and Richard Jow and will spend several months this year at ARL testing the properties of the salts

Université Paris-Sud & Hunter College of CUNY -

Patrick Judeinstein and Steve Greebaum have performed NMR diffusion measurement on the ILs

**Chalmers University, Sweden** – Patrik Johansson is utilizing the known LiDFOB solvate structures to computationally analyze the Raman and IR vibrational bands for the different DFOB<sup>-</sup> solvate structures



### **Future Work**

- Continue with the phase diagram characterization of LiBF<sub>4</sub> and LiDFOB with a wide variety of solvents extend this to include LiPF<sub>6</sub> and additional organoborate anions
- Utilize Raman spectroscopy to further characterize the solvent and anion interactions in both the solid and liquid state...correlate this work with the phase diagrams and solvate crystal structures
- Measure the transport properties (viscosity, conductivity, diffusion coefficients) of the solvent-LiX mixtures to determine the link between properties and structure (solvent and anion)
- Prepare/characterize ILs based upon the DFOB- anion with varying cations – prepare phase diagrams of IL-LiX mixtures
- Test solvent-LiX (nitrile/dinitrile) and IL-LiX mixtures in half and full cells



### **Summary**

- Phase diagrams have been prepared for (solvent)<sub>n</sub>-LiBF<sub>4</sub> and -LiDFOB mixtures to characterize the solid-liquid thermal phase behavior these diagrams, in concert with solvate crystal structures, provide tremendous insight into the solvent...Li<sup>+</sup> and anion...Li<sup>+</sup> interactions
- The phase diagrams and solvate structures also greatly aid in interpreting Raman vibrational spectroscopic data used to characterize the solvent and anion interactions in both the solid and liquid phase this enables the direct exploration of detailed solution structural information a daunting challenge to date
- Characterization of the thermal and transport properties ( $T_{\rm m}$ , density, viscosity, conductivity, diffusion coefficients) of ILs is underway



### **Acknowledgements**



#### **Researchers:**

- Sam Delp (postdoctoral fellow)
- Joshua Allen (graduate student)
- Sang-Don Han (graduate student)

Dr. Venkat Srinivasan, the staff at LBNL, the BATT Program and the U.S. DOE's Vehicle Technologies Program are gratefully acknowledged for support for this research